



Exceptional Grade for
Broad-Range Applications

Plexiglas® G

CELL-CAST ACRYLIC SHEET

Premium-grade Plexiglas® G cell-cast acrylic sheet satisfies the requirements of nearly all high performance applications. Colorless Plexiglas® G acrylic sheet carries a 10-year limited warranty on light transmission. It is available in a broad range of colors and patterns.

Plexiglas® G acrylic sheet is a versatile material that has many residential, commercial, industrial and professional uses. Typical applications include:

- Architectural glazing
- Optical lenses
- Pediatric incubators
- Aquariums
- POP displays
- Hockey rinks
- Industrial and school glazing
- Skylights
- Furniture
- Outdoor signs

PLEXIGLAS®

BY ARKEMA

- High Performance Cell-Cast Acrylic Sheet
- Exceptional Optical Clarity
- Weather Resistant
- Lightweight – Half the weight of glass
- Can be easily fabricated and thermoformed
- Available in transparent, translucent, and opaque colors
- Thickness range from 0.118" - 2.00"
- Sheet sizes range from 48" x 96" to 74" x 99"

COLOR OFFERING

Plexiglas® G acrylic sheet is available in more than 23 different colors. Visit our chips gallery at www.plexiglas.com/gallery to see our wide range of color offerings.

TYPICAL STANDARD PROPERTIES - Plexiglas® G Acrylic Sheet

PROPERTIES	TEST METHOD	UNIT	VALUE
PHYSICAL			
Nominal Thickness for data unless otherwise noted		in	0.236"
Specific Gravity	ASTM D-792	---	1.19
Rockwell Hardness	ASTM D-785	M scale	100
Water Absorption (24 hr immersion @ 73°F) ¹	ASTM D-570	%	0.2
Water Absorption (Long Term Equilibrium – 28 days @ 212°F) ¹	ASTM D-570	%	0.8
Poisson's Ratio	N/A	---	0.35
OPTICAL			
Refractive Index (ND @ 73°F)	ASTM D-542	---	1.49
Luminous Transmittance ¹	ASTM D-1003	%	92.0
Haze ¹	ASTM D-1003	%	< 2.0
MECHANICAL			
Tensile Strength, maximum	ASTM D-638	psi	10,500
Tensile Strength, yield	ASTM D-638	psi	10,500
Tensile Elongation	ASTM D-638	%	4.9
Tensile Modulus of Elasticity	ASTM D-638	psi	450,000
Flexural Strength, maximum	ASTM D-790	psi	16,000
Flexural Modulus of Elasticity	ASTM D-790	psi	450,000
Notched Izod Impact @ 73°F (23°C)	ASTM D-256	ft-lb / in	0.3
Un-notched Charpy @ 73°F (23°C)	ASTM D-256	ft-lb / 0.5"x1" section	7.0
THERMAL			
Deflection Temperature under Flexural Load @ 264psi – unannealed ¹	ASTM D-648	°F	205
Coefficient of Thermal Expansion at 60°F	ASTM E-831	in / in / °F x 10 ⁻⁵	3.9
Coefficient of Thermal Conductivity	ASTM C-177	BTU / (hr)(ft ²)(°F/in)	1.3
U-value (summer gain, winter loss)	N/A	BTU / (hr)(ft ²)(°F/in)	0.89, 0.96
Specific Heat Capacity at 77°F	N/A	BTU / (lb °F)	0.35
Maximum Recommended Continuous Service Temperature	N/A	°F	180 – 200
Recommended Thermoforming Temperature	N/A	°F	290 – 360
CRAZE RESISTANCE			
Constant Stress Craze Resistance, IPA ⁵	Modified ARTC Method – Mil P-6997	psi	2,100
Constant Stress Craze Resistance, Aromatic / Alcohol Blend ⁵	Modified ARTC Method – Mil P-6997	psi	1,700
FLAMMABILITY³ & SPECIFICATION COMPLIANCE			
Horizontal Burn Rate ^{1,2}	ASTM D-635	in / min	< 1.0
Smoke Density	ASTM D-2843	%	1.0
Self Ignition Temperature	ASTM D-1929	°F	860
Surface Burning Characteristics – Flame Spread	CAN/ULC-S102.2-07 File R16788	---	135 (0.125" - 0.250")
Surface Burning Characteristics – Smoke Developed	CAN/ULC-S102.2-07 File R16788	---	> 500 (0.125" - 0.250")
Plastics Component – QMFZ2.E39437 - Flammability Classification	UL 94	---	94HB (≥ 0.060")
Plastics Component – QMFZ2.E39437 - Outdoor Suitability	UL 746C	---	f1 (≥ 0.060" Colorless) f2 (≥ 0.060" ALL)
International Building Code	IBC 2606.4	---	CC2 (0.118" – 0.944")
International Residential Code	IRC 308.3	---	CC2 (> 0.125")
American National Standard for Safety Glazing	ANSI Z97.1	---	PASS (≥ 0.080")
FMVSS 205 – Federal Motor Vehicle Safety Glazing	ANSI Z26.1	---	AS-5, AS-6, AS-7
FAA (FAR) Section 25.853	Appx F, Part 1, Paragraphs (a)(1)(iv), Procedure (b)(5) 15 second horizontal burn	---	PASS (0.118" – 0.472")
Standard Specification for PMMA Acrylic Plastic Sheet	ASTM D-4802	---	Category A-1, Finish 1

Data given are average values and should not be used for specification purposes.

1. This property will change with thickness. The value given is for the thickness indicated in the column heading unless otherwise noted.
2. Tests performed on 0.118" thickness.
3. Flammability tests are small scale tests and may not be indicative of how materials will perform in an actual situation.
4. Conditioned for 24 hours at 122°F
5. The values are after the material has been heated for forming.

For a complete listing of physical properties, go to www.plexiglas.com to download a copy of the Plexiglas® Acrylic Sheet General Information and Physical Properties brochure.

Plexiglas® acrylic plastic is a combustible thermoplastic. Observe fire precautions appropriate for comparable forms of wood and paper. For building uses, check code approvals. Impact resistance is a factor of thickness. Avoid exposure to heat or aromatic solvents. Clean with soap and water. Avoid abrasives.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See MSDS for Health & Safety Considerations.
Altuglas® and Plexiglas® are registered trademarks of Arkema.
©2012 Arkema Inc. All rights reserved.

Altuglas International
Arkema Inc.
100 PA Rt. 413
Bristol, PA 19007
TEL 800.523.7500
FAX 215.826.2698
www.altuglasint.com
www.plexiglas.com